



1318 Tape

Polyester Film Tape with Acrylic Pressure-Sensitive Adhesive

Data Sheet

Product Description

3M™ 1318 Tape is a polyester film tape with acrylic pressure-sensitive adhesive. It has excellent flagging resistance and solvent resistance, making it well suited for applications where cleaning solvents and mineral oil are present. It consists of materials that are represented in many UL Recognized Insulation Systems and has a UL 130°C temperature rating. It offers good wet grab, excellent shelf life, smooth, even unwind and is suitable for printing and use on automated equipment.

- UL Recognized Class 130°C
- Excellent flagging resistant
- Printable
- Solvent resistant without thermosetting
- Excellent shelf life

Applications

3M 1318 Tape is especially suited for applications such as wrapping coils, capacitors, wire harnesses, transformers, shaded pole motors and fractional horsepower motors.

Colors

3M 1318 Tape is available in yellow, white and black.

UL Component Recognition

UL recognized for use at temperatures not exceeding 130°C. UL File Number E17385, Guide OANZ2. Underwriters Laboratories (UL) recognized products are evaluated for use as components of end-product equipment that is listed or classified by UL. To achieve Underwriters Laboratories recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component or products.

Typical Properties	1 Mil Film	2 Mil Film
Adhesive	Acrylic	Acrylic
Backing	Polyester Film	Polyester Film
Backing Thickness ¹	One mil (25 micron)	Two mils (50 micron)
Total Thickness	2.5 mils / 0,063 mm	3.3mils / 0,083 mm
Colors - Designation	Y, W, Blk	Y, W, Blk
Temperature Class	130°C/266°F	130°C/266°F
Dielectric Breakdown ¹	5,500 Volts	7,000 Volts
Insulation Resistance ¹ (megohms)	>1 x 10 ⁶	>1 x 10 ⁶
Breaking Strength ¹	25 lbs./in (44N/10mm)	50 lbs./in (88N/10mm)
Elongation ¹ (% at break)	100	110
Electrolytic Corrosion Factor ²	1.0	1.0
Adhesion to Steel ¹	30 oz/in (3,3N/10mm)	30 oz/in (3,3N/10mm)
Printable	Yes	Yes
CTI Material Group	I	I

Note: Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.

*Footnote:

¹Test method ASTM D 1000

³M Test Method-Available on request.

3M is a trademark of 3M.

Important Notice

All statements, technical information, and recommendations related to Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized

officer of Seller. The statements contained herein are made in lieu of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY, INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY, FOR ANY INJURY OR FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS THAT WERE DEFECTIVE.



Electrical Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
800-676-8381
<http://www.3m.com/elpd>

© 3M 1998
78-8124-4749-4(A)